



**COMMERCIAL - TECHNICAL DATA / Tecnologia**

**FABRIC NAME**

**DRILL MAGNUM**

**COMP: 100% COTTON**

**H.S CODE 5209220000**

**Test Method for Woven Fabrics**

**STANDARD ( WHITE 00/PFD)**

| Width / Ancho<br>NTC 228-2011   | Phisic / Fisico     | In            | Cms |
|---|---------------------|---------------|-----|
|   |                     | Useful / Util | 67  |
| Weight /Peso<br>ASTM D 3776-2009  |                     | Oz/syd        | Gsm |
|   |                     | 7.7           | 260 |
| Shrinkage / Cambio dimensional (%)<br>AATCC 135-2004 / IN504-15   | Lenght / Longitud   | 4%            |     |
|   | Trans / Transversal | 4%            |     |
| Spirality after laundry / Viraje despues del lavado (%)<br>ISO16322-2-2005  | Lenght / Longitud   | 2%            |     |
|   | Trans / Transversal |               |     |
| Color fastness to wash / Solidez al lavado (gray scale)<br>AATCC 61-2007  | Change / Cambio     | 4             |     |
|   | Stain / Transf      | 4             |     |
| Dye transfer to storage. Option II (gray scale) / Transferencia del color por almacenamiento. Opcion II<br>AATCC 163-2007 | Stain / Transf      | 4             |     |
| Color fastness to light (gray scale) / Solidez a la luz<br>BS 1006-1990   | Change / Cambio     | 3             |     |
| Color fastness to crocking (gray scale) / Solidez al frote<br>AATCC 8-2007  | Dry / Seco          | 4             |     |
|   | Wet / Húmedo        | 3             |     |
| Color Fastness to perspiration (gray scale) / Solidez a la transpiración<br>AATCC 15-2007                                 | Change / Cambio     | 4             |     |
|   | Stain / Transf      | 4             |     |
| Pilling / Pilling (Photographic)<br>NTC 2051-2 / 2003   |                     | 3             |     |
| Type of fabric / Tipo de tejido   |                     | Woven         |     |

**Recommendations:**

